

## JT 8300 WM-RT Dot

### PRODUCT DESCRIPTION

Monomeric calendered self-adhesive printing media with dotted adhesive.

**Face Material:** 120 µm white matt PVC

**Adhesive:** Emulsion acrylic removable transparent dotted

**Liner:** Clay Coated 140g/sqm

### TYPICAL USE

Short-term indoor application for communication and advertising campaigns, discounts, promotional activities, product launches, trade shows.

Compatible on glass, alubond and various smooth flat surfaces.

### PROCESSING

Especially designed for solvent based, eco-solvent, mild solvent, Latex and UV\* inkjet printing on wide-format printing equipment.

JT 8300 WM-RT Dot should not be laminated.

To achieve the best possible print quality, please make sure that the correct ICC profiles or printer settings are used.

Profiles can be obtained from our subsidiaries or distributors, or can be downloaded from: [www.mactacgraphics.eu](http://www.mactacgraphics.eu)

For further information on printing, application and removal, please refer to "TB 4.1 Guidelines on handling, converting and applying Mactac Digital media".

\*Not compatible with UV-Gel inks.

To ensure application suitability, always test the proposed construction under actual application and end-use conditions before going into full production.

### SHELF LIFE

2 years when stored at 15 to 25°C and ± 50 % relative humidity (in the original packaging).

### PHYSICAL PROPERTIES (TYPICAL VALUES)

Average Values Test Method

| Thickness   |                  |           |
|---|------------------|-----------|
| Face (microns)                                    | 120 µm           | ISO 534   |
| Adhesive data, 23°C (N/25 mm)                     |                  |           |
| Peel adhesion on glass                            |                  |           |
| - Quick tack                                      | 3.8              | FTM9      |
| - 24 hour residence                               | 2.5              | FTM1      |
| Dimensional stability                             |                  |           |
| Shrinkage (48 hours at 70°C applied on Aluminium) | Max. 0.5 mm      | FTM14     |
| Temperature ranges                                |                  |           |
| Minimum application temperature (°C)              | + 10°C           |           |
| Service temperature range (°C)                    | - 20°C to + 70°C |           |
| Certifications                                    |                  |           |
| Fire certification                                | B-s2, d0         | EN13501-1 |

### EXPECTED DURABILITY

#### Central Europe Zone 1

|             |              |            |
|-------------|--------------|------------|
| Unprocessed | Up to 1 year | ISO 4892-2 |
|-------------|--------------|------------|

Note : Exposure to severe temperatures, ultraviolet light, and/or conditions in Southern European countries, tropical, sub-tropical or desert regions will cause more rapid deterioration. This also applies to polluted areas, high altitudes and south-facing exposure.

#### DISCLAIMER

Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has

independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>. Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.

**DUPLI DATA**  
NUMÉRIQUEMENT VOTRE  
[www.dupli-data.fr](http://www.dupli-data.fr)